



SEABROOK



SBD-146
D Action Yellow




SBD-136
D White



SB-120
Chalk



SBD-135
D Sea White



SBD-137
D Gel White



SB-111
Moonlite




SB-116
Light Glacier



SBD-138
D Seashell



SB-112
Sea White




SB-110
Marble



SB-122
Stinger Bisque



SB-121
Stinger Cream



SB-109
Porcelain



SB-119
Marigold



SB-145
Hot Orange



SB-103
American Beauty



SB-101
Ruby



SB-147
Lime



SB-118
Deep Sea



SB-139
Blue



SBD-141
D Purple



SB-108
Midnight



SBD-106
D Nu Teal



SB-113
Forest



SB-102
Ebony

Specifications

- Roll Width: 54 inches
- Roll Length: 40 yards
- Weight: 30.75 +/- 2 oz per linear yard
- Thickness: 42 +/- 5 mils
- Cold Crack: -25°F

Abrasion Resistance

No Significant wear after 250,000 double rubs with #10 cotton duck using the Wyzenbeek test method.

Feature and Benefits

Mildew resistant, Made in North America, Bromine-free, No halogenated flame, Retardants (HFRs), REACH compliant, RoHS compliant, Non toxic, No heavy metals, No mercury, No bisphenol A (BPA), No ozone depleting chemicals, No PBT's (persistent bio accumulative and toxic chemicals), Contains bio-based renewable ingredients, Formulated without ortho-phthalates, 650 Hours QUV

Flame Resistance

Manufactured to meet the following flammability* requirements:

- CA TB 117-2013
(Section 1 - Cover Fabric)
- UFAC Class 1
- NFP 260
- IMO MSC 88/26/ADD. 2 PART 8
(3.1 and 3.2)

*This term and corresponding data refer to the typical performance in the specific test indicated. They should not be construed to imply the behaviour of this or any other material under actual fire conditions.

Content and Backing

Vinyl, Backing: 100% Polyester Mellohide

Recommended Applications

Auto/Marine Aftermarket, Marine & Recreational Products, Marine Exterior, Marine Interior

*The specifier must comply with all applicable building codes, as well as state and federal regulations.

Care and Cleaning Instructions

To prevent build up of dirt and contaminants, which may cause permanent staining, periodic cleaning is highly suggested. The frequency of cleaning is dependent upon the environmental conditions the material is subjected to.

For normal cleaning: Most stains can be easily cleaned using warm, soapy water and clear water rinses. Moderate scrubbing with a medium bristle brush will help loosen soiling materials from the depressions of embossed surfaces. For more stubborn stains, use Formula 409® commercially available cleaner in accordance with the manufacturer's instructions. Full strength rubbing alcohol or mineral spirits* may be tried cautiously as a last resort on very stubborn stain, if the above suggestions do not work. Indiscriminate use of any solvent, or solvent containing cleaner, can severely damage or discolor vinyl. Always follow with a clear water rinse after cleaning with solvents.

Note: Detergents should never be used on a regular or repeated basis for normal cleaning. Morbern recommends repeated rinsing with clear water after any cleaning procedure. When opening a new container, please test the cleaner in an inconspicuous area as cleaning manufacturers may change formula without notice. Morbern cannot be responsible when unknown changes are made by the manufacturer of the cleaner to their formulations between our 6-month verification intervals.

*Caution: Exercise care as these solvents are flammable. Use only small quantities of solvents and keep clear of any sources of ignition. Wear protective gloves and ensure cleaning takes place in a well ventilated area.



miamicorp.com

miami[™]
CORPORATION

| 800.543.0448