

Stamoid Light F4128	Stamoid Open F4463	Stamoid Heavy Cover F4313	Stamoid Top F3933
------------------------	-----------------------	------------------------------	----------------------

## Technical properties - Características técnicas

## Standards Normas

Coating Recubrimiento	1 side PVC 1 cara PVC	2 sides PVC 2 caras PVC	1 side PVC 1 cara PVC	2 sides PVC 2 caras PVC	
Base cloth Soporte	280 Dtex PES HT	1,100 Dtex PES HT	1,100 Dtex PES HT	280 Dtex PES HT	
Weight Peso	8.8 oz/sq.yd 300 g/m <sup>2</sup>	19.2 oz/sq.yd 650 g/m <sup>2</sup>	15.3 oz/sq.yd 520 g/m <sup>2</sup>	12.7 oz/sq.yd 430 g/m <sup>2</sup>	EN ISO 2286-2
Length of rolls Longitud del rollos	32.81-54.68 yd 30 - 50 lm	32.81 yd 30 lm	32.81 yd 30 lm	32.81 - 54.68 yd 30 - 50 lm	
Thickness Espesor	360 microns 0,36 mm	610 microns 0,61 mm	590 microns 0,59 mm	380 microns 0,38 mm	

## Physical properties - Propiedades físicas

Tensile strength (warp/weft) Resistencia a la rotura (urdimbre/trama)	315/315 lbs/2 in 140/140 daN/5 cm	674/629 lbs/2 in 300/280 daN/5 cm	719/781 lbs/2 in 320/350 daN/5 cm	292/292 lbs/2 in 130/130 daN/5 cm	EN ISO 1421
Tear strength (warp/weft) Resistencia al desgarro (urdimbre/trama)	16/18 lbs/2 in 7/8 daN	76/76 lbs/2 in 34/34 daN	16/18 lbs/2 in 7/8 daN	16/18 lbs/2 in 7/8 daN	DIN 53.363
Color light fastness Solidez del color a la luz	>4/5 (1,000 h) >4/5 (1 000 h)	≥7 (Xenotest 750 hours) ≥7 (Xenotest 750 horas)	>4/5 (1,000 h) >4/5 (1 000 h)	>4/5 (1,000 h) >4/5 (1 000 h)	QUVA test according ASTM G 154
UV Filtration Filtración UV	UPF 50+				EN 13758-1 +A1
Mold resistance Resistencia al moho	Degree 0, excellent Grado 0, excelente				EN ISO 846-A
Extreme working temperatures Temperaturas extremas de uso	-4°F / +158°F -20°C / +70°C				

## Management system - Sistemas de gestión

Quality - Calidad: ISO 9001 • Environment - Medio ambiente: ISO 14001 • Energy - Energía: ISO 50001 only for F4128 - solo para F4128

## Certifications, labels - Certificados, etiquetas

Smart Coating  
Technology



For - Para F4128 & F4313



<sup>1</sup> These products don't contain intentionally added PFAS (these products were not formulated or intended to contain a PFAS that impacts a specific function or characteristic to the product).

<sup>1</sup> Estos productos no contienen PFAS añadidos intencionadamente (estos productos no fueron formulados o destinados a contener un PFAS que repercute en una función o característica específica del producto).

<sup>2</sup> Summarizes the group's CSR project focused on human, to align economic performance and positive impact.

<sup>2</sup> Resume el proyecto de RSC del grupo centrado en lo humano, para alinear rendimiento económico e impacto positivo.

The technical data above are average values with a +/- 5% tolerance. The buyer of our products is fully responsible for their application or their transformation concerning any possible third party. The buyer of our products is responsible for their implementation and installation in compliance with standards, codes of practice and safety regulations in force in destination countries. To ensure warranty effectiveness, refer to warranty certificate concerned available on demand. The values quoted above represent results of tests performed in compliance with common design practices and are provided for information only to enable customers to make the best use of our products. Our products are subject to changes prompted by technological developments. We reserve the right to modify their characteristics at any time. The buyer of our products is responsible for checking the validity of the above data. The colours and textures presented are included for information only.

Los datos técnicos indicados son valores medios con una tolerancia de +/- 5%. El comprador de nuestros productos es responsable de su aplicación o tratamiento con respecto a cualquier derecho de terceros. El comprador de nuestros productos también es responsable de su uso e instalación de acuerdo con las normas, reglas del arte y reglamentos de seguridad del país de destino. Para la garantía contractual, consulte nuestro texto de garantía. Los valores mencionados en este documento son los resultados de las pruebas de acuerdo con las prácticas en el campo de los estudios, se dan como una indicación con el fin de permitir a nuestros clientes el mejor uso de nuestros productos. Nuestros productos están sujetos a cambios como resultado del progreso técnico y nos reservamos el derecho de modificar sus características en cualquier momento. Es responsabilidad del comprador de nuestros productos comprobar la validez de los datos anteriores. Los colores y texturas presentadas están dadas a título indicativo.